

History of Tile Fixing

History of Tile Fixing – Concise Study Notes

1. Early Beginnings (Pre-historic to Antiquity)

Period	Region	Materials & Techniques	Key Points
Pre-historic	Near East, Mediterranean	Clay tablets baked in open fires; simple mud-based mortars (lime + sand) used to adhere pieces to walls and floors.	First evidence of decorative surfaces; tiles were more “painted” than fixed.
Ancient Egypt (c. 3000 BC)	Nile Valley	Sun-dried mud bricks with glazed ceramic tiles; gypsum-based mortars for fixing.	Tiles served both ornamental and protective functions in tombs and temples.
Mesopotamia & Persia	Mesopotamia, Persia	Fired clay tiles set in lime-sand mortars; early use of “tesserae” for mosaics.	Development of patterned mosaics required a reliable bonding medium.
Classical Greece (c. 500 BC)	Greece	Marble and terracotta tiles fixed with lime-based mortars; use of “pozzolan” (volcanic ash) in some coastal areas.	Introduction of geometric patterns; mortar recipes began to be recorded by Vitruvius.
Roman Empire (c. 200 BC – 5 AD)	Europe, North Africa, Middle East	Roman pozzolanic mortar (lime + volcanic ash + sand) – strong, water-resistant; use of hydraulic lime for baths and aqueducts.	Standardized tile sizes (e.g., 30×30 cm “opus tessellatum”). The Romans spread the technique throughout their empire.

2. Medieval & Renaissance Developments (5th – 17th centuries)

Era	Region	Innovations
-----	--------	-------------

History of Tile Fixing

Early Middle Ages	Europe (especially Italy & France)	Re-use of Roman mortar recipes; introduction of lime plaster mixed with animal hair for added tensile strength.
Gothic Period	Central Europe	Use of stone-cutting for floor tiles; mortar enriched with chalk for smoother finish.
Renaissance	Italy, Spain, Portugal	Terracotta tiles mass-produced in Valencia and Lombardy; introduction of tin-glazed tiles (Maiolica) that required a more adhesive mortar to hold the glaze-rich surface.
Northern Europe	Netherlands, England	Development of cobblestone paving using sand-lime mortars; early “dry-set” methods for exterior paving stones.

Key takeaway: The period saw a transition from purely functional bonding agents to mortars that also accommodated decorative glazes and varied tile substrates.

3. The Industrial Age (18th – 19th centuries)

Century	Breakthroughs	Impact on Tile Fixing
18th?C	Portland cement (invented 1824 by Joseph Aspdin)	Provided a stronger, faster-setting binder than lime alone; early “cement mortars” began to replace traditional lime mortars for floor tiles.
Early 19th?C	Mechanical tile presses and mass production of ceramic tiles (e.g., Minton, Wedgwood)	Uniform tile dimensions demanded consistent mortar mixes; standardization of sand-to-cement ratios (1:3 to 1:4) for floor installations.
Mid?19th ?C	**Hydraulic	